

**AMENDMENT TO THE CLAIMS**

The listing of claims will replace all prior versions, and listings, of claims in the application:

1.(Previously presented) A heat shrinkable polyester film, which satisfies the following requirements, (A) to (C):

(A) when a square test piece cut off from said heat-shrinkable polyester film in a size of 10 cm x 10 cm is immersed in hot water at 70°C for 5 seconds, subsequently in water at 25°C for 10 seconds, and withdrawn, the heat shrinkage percentage of the test piece in the maximum shrinkage direction is 10 to 50%;

(B) when a square test piece cut off from the heat-shrinkable polyester film in a size of 10 cm x 10 cm is immersed in hot water at 85°C for 5 seconds, subsequently in water at 25°C for 10 seconds, and withdrawn, the heat shrinkage percentage of the test piece in the maximum shrinkage direction is 70% or more and that in the direction orthogonal thereto, 10% or less; and

(C) when a square test pieces cut off from the heat-shrinkable polyester film and the film thereof previously 10% heat shrunk in the maximum shrinkage direction in a size of 10 cm x 10 cm are immersed in hot water at 95°C for 5 seconds, subsequently in water at 25°C for 10 seconds, and withdrawn, the heat shrinkage percentage of the test pieces in the maximum shrinkage direction are designated respectively as  $X_0$  (%) and  $X_{10}$  (%), the difference in heat shrinkage percentage  $\Delta$  (%) calculated according to the following equation is 10 to 20%,

$$\Delta = X_0 - X_{10}.$$

2.(Original) A heat shrinkable polyester film according to claim 1, wherein when the heat shrinkage stress in the maximum shrinkage direction of the film thereof previously 10% heat-shrunk in the same direction is determined under the condition of a temperature of 90°C, a flow rate of heated air of 5 m/sec, a width of the test piece of 20 mm, and a

distance between chucks of 100 mm, the maximum heat shrinkage stress is 7 MPa or more.

3. (Previously presented) A heat shrinkable polyester film according to claim 1, wherein when a thickness variation of a test piece thereof having a length of 50 cm and a width of 5 cm is determined in the maximum shrinkage direction of the film, the thickness distribution calculated according to the following equation is 6% or less,

Thickness distribution = [(Maximum thickness – Minimum thickness)/Average thickness] x 100.

4. (Original) A heat shrinkable polyester film according to claim 1, wherein the melt resistivity thereof is  $0.70 \times 10^8 \Omega \cdot \text{cm}$  or less at 275°C.

5. (Currently amended) A heat-shrinkable label ~~characterized by using~~ comprising said heat-shrinkable polyester film according to claim 1.